

# Provisional Technical Datasheet



Polypropylene Homo polymer

HF010

TQPP Films

## Product Characteristics:

Mangpol HF010 is a Polypropylene Homo polymer produced by latest solvent free gas phase polymerization using Novolen Technology. This polymer is primarily suitable for Tubular water quench film applications.

HF010 combines exceptional processability with superior Slip, Anti Blocking Properties, Excellent Clarity and Gloss.

## Recommended Applications:

- Textile over-wraps, garment bags.
- Packaging items for foodstuffs, snack foods, grocery.
- General Purpose packaging.

## Typical Properties

Sr. No.	Properties	Test Method	Units	Typical Values
1.	Melt Flow Index ( $I_{2.16}$ @230°C)	ASTM D 1238	g / 10 min	10.5
2.	Tensile Strength at Yield	ASTM D 638 (Type 1)	MPa	34
3.	Tensile Elongation at Yield		%	9
4.	Flexural Modulus	ASTM D 790	MPa	1500
5.	Izod Impact Strength	ASTM D 256	J /m	30
6.	Vicat Softening Point (10N)	ASTM D 1525	°C	154
7.	Heat Deflection Temperature (0.455MPa)	ASTM D 648	°C	85

- All the mechanical properties are as per ASTM D638 Type 1 injection molded specimen prepared in accordance with ASTM D 4101.

## Typical Processing Temperature

- Barrel Temperature: 180 - 230°C.
- Die Temperature: 190 – 210 °C.

## Handling & Storage

Bags should be stored in dry & dust free environment at temperature below 50°C. Avoid direct exposure to sunlight & heat to avoid quality deterioration.

**Disclaimer:** The above typical properties are not to be construed as Specifications and may change without any prior notice. The user will solely be responsible for any intended process / product usage and MRPL does not guarantee or undertake any responsibility for any consequential damage or loss based on the information given above.

Mangalore Refinery & Petrochemicals Limited, Kuthethoor, P.O.: Via Katipalla, Mangalore, India, 575030, Corporate website: [www.mrpl.co.in](http://www.mrpl.co.in)